



**Cosmos Lac AE**

1 Pindou str.  
17672 Kallithea, Athens, Greece.  
Tel.: +30 2109570222 -  
Fax: +30 2109566671  
factory@cosmoslac.com  
www.cosmoslac.com

## Technical Data Sheet

<b>PRODUCT</b>	<b>COSMOS LAC SEALER Spray N260-1-2-3</b>
<b>DESCRIPTION/USES</b>	Rubberized coating that insulates and seals leaks. It creates a thick elastic layer that has high resistance to weather conditions and UV radiation. Ideal for roofs, balconies, drainage pipes, gutters, mezzanines. Applies to metal, vinyl, plastic, PVC, cement. It can be over painted with any paint after it has dried.
<b>Available colours</b>	Black, White, Grey, Brick
<b>Viscosity</b>	25-35 sec (Flow Cup DIN4, 20°C)
<b>Density</b>	1.0 ± 0.03 g/L (Density Cup 100cm <sup>3</sup> /20°C, ASTM D – 1475)
<b>Flash Point</b>	-104 °C (based on propellant)
<b>V.O.C.</b>	595 g/L
<b>Drying time</b>	Touch (20°C, Humidity<65%): 10-15min Through dry (20°C, Humidity <65%): 1h Maximum hardness: 24h
<b>Coverage</b>	3m <sup>2</sup> /L
<b>Gloss</b>	<10 GLOSS UNIT/MATTE [GLOSS METER 60°ASTM D –1471]
<b>Can Pressure</b>	4bar (20°C), 8 bar (50°C)
<b>Contents</b>	500ml
<b>Application</b>	Surfaces must be clean, dry, and free from grease. Cover the areas that need to be protected with tape. Shake the container for two minutes. Spray on a test area to check the distance (20-30cm) and technique of spraying. Apply at least a second layer after 15 minutes. Best application temperature: 10oC - 25oC
<b>After use</b>	Spray holding the can, inverted for 3". Clean the caps with solvent.
<b>Storage</b>	5-35°C. Do not put in vehicles.

ISSUED 30 October 2023, factory@cosmoslac.com, V02 (Replaced 1)